

1 **SECTION 8-09, RAISED PAVEMENT MARKERS**

2 **August 4, 2003**

3 **8-09.3(3) Adhesive Preparation**

4 This section is revised to read:

5

6 Epoxy adhesive shall be maintained at a temperature of 60 F to 85 F before use and
7 during application.

8

9 Component A shall be added to component B just before use and mixed to a smooth
10 uniform blend. The unused mixed adhesive shall be discarded when polymerization
11 has caused stiffening and reduction of workability.

12

13 Bituminous pavement marker adhesive shall be indirectly heated in an applicator with
14 continuous agitation or recurring circulation. Adhesive temperature shall not exceed the
15 maximum safe heating temperature stated by the manufacturer. The Contractor shall
16 provide the Engineer with manufacturers written instruction for application temperature
17 and maximum safe heating temperature.

18

19 **8-09.3(4)B Asphalt Adhesives**

20 The second paragraph is revised to read:

21

22 Bituminous adhesive shall be applied at temperatures recommended by the
23 manufacturer.